

# SIPERNAT® 622 S

## Product Information

### Characteristic physico-chemical data<sup>\*)</sup>

Properties and Test Methods	Unit	Value
<b>Specific surface area (N<sub>2</sub>)</b> Multipoint following ISO 9277	m <sup>2</sup> /g	175
<b>Particle Size, d<sub>50</sub></b> Laser diffraction following ISO 13320-1	µm	13.0
<b>Tamped density</b> not sieved following ISO 787-11	g/l	125
<b>Loss on drying</b> 2 h at 105 °C following ISO 787-2	%	≤ 7.0
<b>Loss on ignition<sup>2)</sup></b> 2 h at 1000 °C following ISO 3262-1	%	4.5
<b>pH value</b> 5 % in water following ISO 787-9		6.5
<b>DOA absorption<sup>1)</sup></b> following Evonik method	ml/100 g	220
<b>SiO<sub>2</sub> content<sup>3)</sup></b> following ISO 3262-19	%	≥ 97
<b>Electrical Conductivity</b> 4 % in water following ISO 787-14	µS/cm	≤ 1000
<b>Sieve residue, Spray 45 µm</b> following ISO 3262-19	%	≤ 1.5
<b>Package size bag (net)</b>	kg	15

1) based on original substance

2) based on dried substance

3) based on ignited substance

\*) The given data are typical values. Specifications on request.

SIPERNAT® Specialty Silica represents a special product range of precipitated silicas, aluminum and calcium silicates.

Careful adjustments of parameters such as surface area, particle size, oil absorption capacity and purity result in products with different properties.

SIPERNAT® 622 S is a fine particle silica with medium surface area and high oil absorption capacity (DOA). It can beneficially used as flow aid/anticaking agent.

### Registrations

CAS-RN of Product	112926-00-8 (ex 7631-86-9)
EINECS (Europe)	registered
ENCS (Japan)	registered
ECL (South Korea)	registered
TSCA (USA) AICS (Australia) PICCS (Philippines) DSL (Canada) IECS (China)	registered
NZIoC (New Zealand)	registered

**Storage properties:** The products should be stored preferable in close original baggage unit under dry conditions at ambient temperature and protected from volatile substances. The best before use date of the product is one year. After this time the product should be processed. For getting sure that the product and application properties, especially at the end of the storage time, have not changed too much, we recommend to prove again moisture up-take of the silica.

---

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

---



**EVONIK**  
INDUSTRIES

**Europe/Middle-East/  
Africa/Latin America**

**Evonik Degussa GmbH**  
Inorganic Materials  
Weißfrauenstraße 9  
60287 Frankfurt am Main  
Germany  
**PHONE** +49 69 218-2613  
**FAX** +49 69 218-62613  
ask-si@evonik.com

**www.evonik.com**

**North America**

**Evonik Degussa Corporation**  
Inorganic Materials  
379 Interpace Parkway  
P. O. Box 377  
Parsippany, NJ 07054-0677  
USA  
**PHONE** +1 888 745-4227  
**FAX** +1 732 981-5310  
ask-si-nafta@evonik.com

**Asia/Pacific**

**Evonik Degussa (SEA) Pte. Ltd.**  
Inorganic Materials  
3 International Business Park  
#07-18 Nordic European Centre  
Singapore 609927  
**PHONE** +65 6 890-6031  
**FAX** +65 6 890-6872  
ask-si-asia@evonik.com

**Evonik. Power to create.**